

## MagChem<sup>®</sup> P98 Dead Burned Milled Magnesium Oxide

| DESCRIPTION | MagChem P98 products are high<br>and dolomitic lime. The products<br>with high density and low reactivi   | are fired in a shaft kil |                 | -                    |
|-------------|---|--------------------------|-----------------|----------------------|
| USES        | MagChem P98 products are well suited for refractory and ceramic applications an applications where a slow, controlled chemical reaction rate is required. |                          |                 |                      |
| COMPOSITION |   |                          | <u>Typical</u>  | <b>Specification</b> |
|             | Magnesium Oxide (MgO), %  |                          | 98.0            | 97.7 min.            |
|             | Silicon Oxide (SiO <sub>2</sub> ), %  |                          | 0.7             | 0.8 max.             |
|             | Calcium Oxide (CaO), %  |                          | 0.95            | 1.1 max.             |
|             | Iron Oxide (Fe <sub>2</sub> O <sub>3</sub> ), %   |                          | 0.15            | 0.3 max.             |
|             | Aluminum Oxide (Al <sub>2</sub> O <sub>3</sub> ), %   |                          | 0.19            | 0.3 max.             |
|             | Loss on Ignition, %   |                          |                 | 0.3 max              |
|             | Typical Screen Sizes  |                          |                 |                      |
|             | % Passing   | <u>1/8"</u>              | <u>-30 Mesh</u> | Pulverized           |
|             | 4 Mesh  | 100                      |                 |                      |
|             |   | 05                       |                 |                      |
|             | 6 Mesh  | 95                       |                 |                      |
|             | 8 Mesh  | 64                       | 100             |                      |
|             | 8 Mesh<br>16 Mesh   | 64<br>16                 | 99.0            | 100                  |
|             | 8 Mesh<br>16 Mesh<br>30 Mesh  | 64                       |                 | 99.8                 |
|             | 8 Mesh<br>16 Mesh   | 64<br>16                 | 99.0            |                      |
|             | 8 Mesh<br>16 Mesh<br>30 Mesh<br>50 Mesh<br>100 Mesh   | 64<br>16                 | 99.0<br>88      | 99.8                 |
|             | 8 Mesh<br>16 Mesh<br>30 Mesh<br>50 Mesh   | 64<br>16                 | 99.0            | 99.8<br>98           |

NOTICE: THE INFORMATION CONTAINED HEREIN IS, TO THE BEST OF OUR KNOWLEDGE AND BELIEF, ACCURATE. ANY RECOMMENDATIONS OR SUGGESTIONS MADE ARE WITHOUT WARRANTY OR GUARANTEE OF RESULTS SINCE CONDITIONS OF HANDLING AND OF USE ARE BEYOND OUR CONTROL; WE THEREFORE, ASSUME NO LIABILITY FOR LOSS OR DAMAGE INCURRED BY FOLLOWING THESE SUGGESTIONS. SELLER WARRANTS ONLY THAT THIS PRODUCT WILL MEET THE SPECIFICATIONS SET FORTH. ANY OTHER REPRESENTATION OR WARRANTY, EITHER EXPRESS OR IMPLIED, IS SPECIFICALLY DISCLAIMED INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE AND OF MERCHANTABILITY. SELLERS AND MANUFACTURERS ONLY OBLIGATION SHALL BE TO REPLACE SUCH QUANTITY OF THE PRODUCT PROVED TO BE DEFECTIVE. BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR USERS INTENDED APPLICATION AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. NEITHER NOR MANUFACTURER SHALL BE LIABLE IN TORT, CONTRACT OR UNDER ANY THEORY FOR ANY LOSS OR DAMAGE, INCIDENTAL OR CONSEQUENTIAL, ARISING OUT OF THE USE OF OR THE INABILITY O USE THE PRODUCT.

Martin Marietta Magnesia Specialties, LLC

8140 Corporate Drive, Suite 220 Baltimore, Maryland 21236 USA Phone: (800) 648-7400 or (410) 780-5500 Fax: (410) 780-5777 Email: MagChem@martinmarietta.com www.magnesiaspecialties.com



QUALITY SYSTEM ISO 9001 CERTIFIED

Copyright © 2015 by Martin Marietta Magnesia Specialties, LLC Version 01/28/15

| PACKAGING | Martin Marietta Magnesia Specialties offers a variety of packaging options, including bags, and bulk sacks. Please contact a sales representative for information on available packaging options. |
|-----------|---|
| STORAGE   | Store in a dry place. Exposure to moisture may cause caking.  |

NOTICE: THE INFORMATION CONTAINED HEREIN IS, TO THE BEST OF OUR KNOWLEDGE AND BELIEF, ACCURATE. ANY RECOMMENDATIONS OR SUGGESTIONS MADE ARE WITHOUT WARRANTY OR GUARANTEE OF RESULTS SINCE CONDITIONS OF HANDLING AND OF USE ARE BEYOND OUR CONTROL; WE THEREFORE, ASSUME NO LIABILITY FOR LOSS OR DAMAGE INCURRED BY FOLLOWING THESE SUGGESTIONS. SELLER WARRANTS ONLY THAT THIS PRODUCT WILL MEET THE SPECIFICATIONS SET FORTH. ANY OTHER REPRESENTATION OR WARRANTY, EITHER EXPRESS OR IMPLIED, IS SPECIFICALLY DISCLAIMED INCLUDING WARRANTIS OF FITNESS FOR A PARTICULAR PURPOSE AND OF MERCHANTABILITY. SELLERS AND MANUFACTURERS ONLY OBLIGATION SHALL BE TO REPLACE SUCH QUANTITY OF THE PRODUCT FOR USERS INTENDED APPLICATION AND USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR USERS INTENDED APPLICATION AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. NEITHER SELLER NOR MANUFACTURER SHALL BE LIABLE IN TORT, CONTRACT OR UNDER ANY THEORY FOR ANY LOSS OR DAMAGE, INCIDENTAL OR CONSEQUENTIAL, ARISING OUT OF THE USE OF OR THE INABILITY TO USE THE PRODUCT.

## Martin Marietta Magnesia Specialties, LLC

8140 Corporate Drive, Suite 220 Baltimore, Maryland 21236 USA Phone: (800) 648-7400 or (410) 780-5500 Fax: (410) 780-5777 Email: MagChem@martinmarietta.com www.magnesiaspecialties.com



QUALITY SYSTEM ISO 9001 CERTIFIED

MagChem<sup>®</sup> is a trademark of Martin Marietta Magnesia Specialties, LLC

Page 2 of 2

Copyright © 2015 by Martin Marietta Magnesia Specialties, LLC Version 01/28/15